

FLAMMABILITY TEST REPORT

Report No.: LEHTX00589407 Date Received: 15/07/11 Date Tested: 19/07/11 Date Issued: 19/07/11


Company Name & Address: BUTE FABRICS LTD
4 BARONE ROAD
ROTHESAY
ISLE OF BUTE
PA20 0DP

Contact Name: SUZANNE MCGROARTY

Sample Details

Order no.: 134783
Description: Troon CF752
Style no.: Not stated
Quality: Not stated
Batch no.: 22896/01
Supplier: Bute Fabrics LTD
Colour(s): 2323
End Use: Upholstery Fabric
Quoted Fibre composition: 85% Pure New Wool, 15% Nylon
Fabric type: Woven
Sample description: Brown / Blue coloured woven fabric

Test Method	Requirement	Result
16 C.F.R. Sec. 1610	State of California Home Furnishings Act, Bulletin 117 Section E- Upholstery Fabrics	Class 1 (Normal flammability)



STEVEN OWEN
(Chemical Technologist)

CAROLE SPOWART
(Flammability Technician)

ANDREW WHITE
(Quality Manager)

SIMON CHEE
(Analytical Lab Manager)

FLAMMABILITY TEST REPORT

Evaluation of test results

The sample submitted for testing is rated as a **Class 1** material (normal flammability) when tested and classified in accordance with procedures and requirements of the Federal Flammable Fabrics Act. Therefore, this fabric meets the standards set forth in the State of California Home Furnishings Act, Bulletin 117 Section E – Upholstery Fabrics.

Test Results

		Face	Back
Test 1	Length	DNI	DNI
Test 2	Length	DNI	DNI
Test 3	Length	DNI	DNI
Test 4	Length	DNI	DNI
Test 5	Length	DNI	DNI
Test 6	Width	DNI	DNI
Test 7	Width	DNI	DNI
Test 8	Width	DNI	DNI
Test 9	Width	DNI	DNI
Test 10	Width	DNI	DNI

DNI – Did Not Ignite

Requirements

1. Raised surface fabric: 7.0 Seconds Minimum Average or Non Ignition.
2. Plain surface fabrics: 3.5 Seconds Minimum Average or Non Ignition.